

EXPERT LABORATORY OL 124

Thákurova 2077/7, Praha 6, 166 29

Phone: +420224357177

E-mail: jiranek@fsv.cvut.cz

No. of copies: 2

Copy No: 1

No. of pages: 3

Page No.: 1

No. of annexes: 0

No. of annexes pages: 0

Order No: 8602600A047**TEST REPORT No: 124041/2026**


upon the test : **Determination of the radon diffusion coefficient
of KÖSTER VAP I 2000 FS carried out in accordance with
the ISO/TS 11665-13**

Client's name and address:**KÖSTER BAUCHEMIE AG**

Dieselstraße 1-10

D-26607 Aurich

Germany

Date of issue: 11.6.2026**Approved by:**

prof. Ing. Martin Jiránek, CSc.
Technical head of OL 124 laboratory

This report can only be reproduced in its entirety; in part only with a written consent of the testing laboratory. The test results refer exclusively to the subject of the test (test sample).

Subject of the test: #KÖSTER VAP I 2000 FS# – an epoxy coating applied to fibre cement board samples

Testing procedure: Determination of the radon diffusion coefficient

Test regulation: ISO/TS 11665-13

Test samples were sampled or manufactured by: Client – results refer to the samples as they were taken over

Date of taking over test samples: 25.5.2026

Samples taken over by: prof. Ing. Martin Jiránek, CSc.

Marking of test samples: 36/26/J (1 – 3)

Manufacturing site of test pieces: –

Date of manufacturing test pieces: –

Test pieces manufactured by: –

Marking of test pieces: –

Test execution date: 3.6.2026 – 10.6.2026

Test execution place: laboratory OL124 – D2044d

Testing device:

Radon detectors TSR-4 of the TERA system (12424)

Measuring system with ionization chambers operating in current mode (12420)

Radon concentration measuring system RM-2 (12428)

Micrometer (12403)

Name of the person who performed the test:

prof. Ing. Martin Jiránek, CSc., Ing. Veronika Kačmaříková, Ph.D.

Potential data on deviations from the test regulation: –

Data on uncertainties of quantitative results: The expanded uncertainties of measurement $\pm U$ mentioned are the product of standard measurement uncertainties and the expansion coefficient $k = 2$, which provides a confidence interval of approx. 95 %.

The report prepared by: Ing. Veronika Kačmaříková, Ph.D.

The report checked by: –

Test samples

The tested coating was applied by the client to cement fibreboard samples. The dimensions of the samples were 135 x 325 mm (effective area 293.10^{-4} m^2) and their thickness varied from 5,33 mm to 5,40 mm. The thickness of the KÖSTER VAP I 2000 FS itself was from 0,41 mm to 0,54 mm. Radon diffusion of the cement fibreboard samples was determined separately (test report 124040/2026).

Test method

Radon diffusion coefficient was determined according to the method A of ISO/TS 11665-13. The tested samples were placed between the source and the receiver containers each with a volume $2,7.10^{-3} \text{ m}^3$. Radon diffuses through the samples from the source container, which is connected to the radon source RF 100, to the receiver containers. Concentrations on both sides of the tested samples are measured continuously by radon detectors TSR-4 of the TERA system (receiver containers) and current mode ionization chambers (source container). Radon diffusion coefficient was derived from the process of fitting the numerical solution to the curves of radon concentration measured in the receiver containers. Numerical solution is based on the one-dimensional time-dependent diffusion equation describing the transport of radon through a two-layer sample, where the diffusion coefficient of only one layer is unknown.

Laboratory conditions

#KÖSTER VAP I 2000 FS# – material

Steady state radon concentration in the source container: $6,3 \pm 0,1 \text{ MBq/m}^3$

Maximum radon concentration in the receiver containers: below the detection limit

Test results

The resulting mean values of determined quantities including expanded measurement uncertainty, are listed in the following table in the form of (mean $\pm$ U).

TESTED MATERIAL	#KÖSTER VAP I 2000 FS#
Rn diffusion coefficient $D \text{ (m}^2/\text{s)}$	$< (5,2 \pm 0,6).10^{-14}$
Rn diffusion length $l \text{ (m)}$	$< (1,6 \pm 0,2).10^{-4}$
Rn resistance $R_{Rn} \text{ (Ms/m)}$	$> 36\,229 \pm 4\,311$

The radon diffusion length was calculated according to the equation $l = \sqrt{D/\lambda}$ and the radon resistance as follows: $R_{Rn} = \frac{\sinh(d/l)}{\lambda \cdot l}$, where $\lambda = 2,1.10^{-6} \text{ s}^{-1}$ and $d = 0,50 \text{ mm} = 0,50.10^{-3} \text{ m}$.

Sampling performed by the client - results refer to the samples as received.

data marked in this way were supplied by the client; OL124 is not responsible for them.

end of the report